

## Flowseal HTS

Flowseal HTS Blank is a 3-component, high solids, low odour, semi-gloss, UV stable, abrasion resistant polyurethane sealer in clear or coloured.

### Uses

Typically used as a high wear UV stable sealer, applied as a floor finish to Flowcrete resin systems.

### Environment & Health

Follow the appropriate Occupational Health and Safety guidelines applicable to the location where the application is undertaken. For more information, please refer to the safety datasheets for the individual components.



#### Solvent Free & Low Odour:

The coating is low in odour and solvent free.



#### Attractive:

Brightens up dull, dark and musty industrial environments.



#### Roller Applied:

Easy to apply with excellent finishing properties.



#### Resistant:

Hard wearing, durable, chemical and abrasion resistant.

### Packaging

The product is supplied in full units as A+B+Pigment or PreTinted A+ B packs.

Base A	7.232 kg	
Hardener B	2.068 kg	
Pigment	0.7kg	
Kit Size	10 kg	7 Ltr
PreTinted Flowcoat OP		
PreTinted Base A	7.93 kg	
Hardener B	2.07kg	
PreTinted Kit Size	10kg	7 Ltr

### Standard Coverage Rates

Flowcoat OP 0.3mm Smooth Finish		
First Coat	0.2kg/m <sup>2</sup>	7m <sup>2</sup> /Ltr
Second Coat	0.2kg/m <sup>2</sup>	7m <sup>2</sup> /Ltr
Flowcoat OP 0.35mm Light Non Slip Finish		
First Coat	0.2kg/m <sup>2</sup>	7m <sup>2</sup> /Ltr
Second Coat	0.2kg/m <sup>2</sup>	7m <sup>2</sup> /Ltr
Non Slip Aggregate*	0.01kg/m <sup>2</sup>	-
Flowcoat OP 1.5mm Non Slip Finish		
First Coat	0.25kg/m <sup>2</sup>	5.5m <sup>2</sup> /Ltr
Non Slip Aggregate	2kg/m <sup>2</sup>	-
Second Coat	0.55kg/m <sup>2</sup>	2.6m <sup>2</sup> /Ltr
*Refer to Technical Data Sheet.		

### Curing Times (at 20°C)

Min Overcoating	8 hours
Max Overcoating	24 hours
Foot Traffic	24 hours
Vehicular Traffic	72 hours
Full Chemical Cure	7 days
*Full chemical resistance is achieved after 5-7 days. ** Do not cover or wash within the first 36 hours of curing.	

## Additional Information

Density	Approx 1.422 kg/l (combined)
Solids Content	Approx 85% (by weight)
Finish	Semi-Gloss
Colour	Refer to Flowcoat OP TDS

## Substrate Requirements

Concrete or screed substrate should be a minimum of 25 N/mm<sup>2</sup>, free from laitance, dust and other contamination. Substrate should be dry to 75% RH as per ASTM F2170 (AS1884:2012). Slab on ground concrete must have an effective damp proof membrane in place.

## Coving

Please refer to Flowtex F1 Coving Mortar for further information.

## Storage

Time	12 Months in Unopened Packs. If longer than 12 Months consult Flowcrete.
Temperature	Storage temperature between 5°C and 35°C.
Protection	Should be stored inside and protected from frost, weather, moisture, direct sunlight and contamination ingress.

## Mixing

The product is supplied in full units as A+B+C. Do not split the components as this may jeopardise the end result. Premix the Base A to redisperse any settlement and pour into a separate container (minimum 10ltr). Add the Pigment (0.75kg) to the Base A and mix using a slow speed drill and helical spinner until the pigment is fully dispersed. Add the Hardener B and Filler C for 90 seconds until a homogenous mixture is obtained, taking care not to entrain air.

## Solvent

Solvent (Xylene / MEK / Acetone) may be added to aid application properties if required.

Add between 2% and 7% solvent (depending on temperature and material viscosity) of Xylene, MEK or Acetone to assist with the application properties.

## Application Temperature

The recommended material and substrate temperature is 15 - 35°C, but no less than 10°C. The temperature of the substrate should exceed the "dew point" by 3°C during application and hardening.

Temperatures should not fall below 5°C in the 24hrs after application.

## Application / Pot Life

Ready-mixed product should be used within 20 minutes at a temperature of 20°C. At higher temperatures (or if left in bucket) the application time is shorter.

Decant mixed product into smaller quantities if applying small/detailed areas.

## Application Method

Please refer to appropriate Flowcoat OP Technical Data Sheet as per required specification.

## Cleaning

Tools and equipment can be cleaned with MEK/Acetone/Xylene. Please refer to SDS when using solvents.

## Additional Notes

1. Maximum overcoat time is 24 hours at 20°C.
2. The product has reached full chemical cure after 7 days at 20°C.
3. The applied colours may differ from the examples shown.
4. Light and vibrant colours may require additional coats to achieve desired results.

5. Flowcrete assumes no responsibility for the application of incorrect colour.
6. It is the applicators responsibility to verify accuracy of colour prior to application. Flowcrete does not bear any responsibility or accept claims for incorrect colour after application of material.
7. It is recommended that top coat colours match base coat colours to achieve desired results.
8. This system is not UV stable and will discolour unless otherwise stated.
9. This system should have no contact with water for 5 days at 20°C or blooming may occur.
10. This system should be installed at 3°C above the dew point.
11. A low temperature/high humidity environment can cause blooming issues.
12. Please ensure application temperature and RH limits are followed.
13. Wind or strong airflow may cause quick curing and drying of the system.
14. Ensure wind or strong airflow is eliminated during application, however adequate safety ventilation should still be followed.
15. Direct heat during application of the system can cause flash curing and potential delamination. Ensure you do not apply this system to substrates with temperatures exceeding 35°C.

## Flowcoat OP

### Additional Information

<b>VOC Content</b>	28 g/L Complies with Green Building Council of Australia Green Star Design & As Built V1.2-13.1.1B Green Star Interiors V1.2-12.1.1B
<b>Density</b>	Approx 1.422 kg/l (combined)
<b>Solids Content</b>	Approx 100% (by weight)
<b>Finish</b>	Smooth, Light Non Slip, Non-Slip Gloss Finish
<b>Colour</b>	Refer to Flowcoat OP TDS

### Storage

<b>Time</b>	12 Months in Unopened Packs. If longer than 12 Months consult Flowcrete.
<b>Temperature</b>	Storage temperature between 5°C and 35°C.
<b>Protection</b>	Should be stored inside and protected from frost, weather, moisture, direct sunlight and contamination ingress.

### Solvent

Solvent (Xylene / MEK / Acetone) may be added to aid application properties if required.

Add between 2% and 7% solvent (depending on temperature and material viscosity) of Xylene, MEK or Acetone to assist with the application properties.

### Packaging

The product is supplied in full units as A+B+Pigment or PreTinted A+ B packs.

<b>Base A</b>	7.232 kg	
<b>Hardener B</b>	2.068 kg	
<b>Pigment</b>	0.7kg	
<b>Kit Size</b>	10 kg	7 Ltr
PreTinted Flowcoat OP		
<b>PreTinted Base A</b>	7.93 kg	
<b>Hardener B</b>	2.07kg	
<b>PreTinted Kit Size</b>	10kg	7 Ltr

### Standard Coverage Rates

Flowcoat OP 0.3mm Smooth Finish		
<b>First Coat</b>	0.2kg/m <sup>2</sup>	7m <sup>2</sup> /Ltr
<b>Second Coat</b>	0.2kg/m <sup>2</sup>	7m <sup>2</sup> /Ltr
Flowcoat OP 0.35mm Light Non Slip Finish		
<b>First Coat</b>	0.2kg/m <sup>2</sup>	7m <sup>2</sup> /Ltr
<b>Second Coat</b>	0.2kg/m <sup>2</sup>	7m <sup>2</sup> /Ltr
<b>Non Slip Aggregate*</b>	0.01kg/m <sup>2</sup>	-
Flowcoat OP 1.5mm Non Slip Finish		
<b>First Coat</b>	0.25kg/m <sup>2</sup>	5.5m <sup>2</sup> /Ltr
<b>Non Slip Aggregate</b>	2kg/m <sup>2</sup>	-
<b>Second Coat</b>	0.55kg/m <sup>2</sup>	2.6m <sup>2</sup> /Ltr
*Refer to Technical Data Sheet.		

### Curing Times (at 20°C)

<b>Min Overcoating</b>	8 hours
<b>Max Overcoating</b>	24 hours
<b>Foot Traffic</b>	24 hours
<b>Vehicular Traffic</b>	72 hours
<b>Full Chemical Cure</b>	7 days
*Full chemical resistance is achieved after 5-7 days. ** Do not cover or wash within the first 36 hours of curing.	